

Quantity discounts apply on multiples of the same item

ORTON PYROMETRIC CONES

Common Firing Temperatures

The Greek letter Delta, or 'Δ', is the commonly used symbol for the word "cone." During firing, cones soften and melt as they are heated, and gravity causes them to bend. It usually takes 15 to 22 minutes for cones to bend fully once they begin melting.

Cone	°F	°C	Firing Type
022.....	1094	590w	
021.....	1143.....	617	
020.....	1180	638	
019.....	1265	695	Mother-of-Pearl
018.....	1337.....	734.....	Gold, Lusters, China Paints, Decals, Enamel
017	1386	763	
016.....	1443	796	
015.....	1485	818	
014.....	1528	838	Glass Fusing
013.....	1578.....	861	
012.....	1587.....	882	
011.....	1623	894	
010.....	1641.....	915	
009.....	1693	930	
08.....	1751.....	956	Soft Bisque for Raku Work
07	1803	987	
06.....	1830	1013	
05.....	1915.....	1044.....	Hobby Ceramic Glazes
04.....	1940	1077	Hobby Ceramic Bisque, Pottery Bisque for Δ6-10 Clay
03.....	2014.....	1104	
02.....	2048	1122	
01.....	2079.....	1138	
1.....	2109.....	1154.....	Sanitary Ware Glaze Firing
2.....	2124.....	1164.....	Sanitary Ware Glaze Firing
3.....	2134.....	1170	
4.....	2167.....	1183	
5.....	2185.....	1207	Stoneware Glazes (beginning of range)
6.....	2232	1243.....	Porcelain Doll Full Bisque Maturity
7	2264	1257	Upper end of Stoneware Glaze range
8.....	2305	1271	
9.....	2336	1280	Pottery Glaze Firing (in wood or fossil-fueled kilns
10.....	2381	1305	and reduction atmospheres)

Temperatures are based on Self-Supporting Cones at 270 °F or 150 °C per hour rate of increase.

Cone numbers originally started at 1 and went to 20. Each higher cone number requires more heat to bend. Higher and lower cones were developed as demand grew. A zero was added in front of the number for cones maturing at temperatures below the original cone 1. Thus Δ01 needs less heat than Δ1, and Δ020 needs less than Δ019. It is important not to mix up the lower maturing cones, whose numbers begin with zero, with the higher maturing cones. Δ06 and Δ6 are not the same!



Cone Prices

1-11 @ 12+ @

SRB ... Junior Cones \$9.40..... \$7.05

- Commonly used in the Dawson Kiln-Sitter.
- Tapered shape gives some flexibility in adjusting the shutoff point.
- Can be used as mini witness cones in tight spaces.
- Melt at slightly higher temperatures than SSBs or LRBs.
- Box of 50

1-11 @ 12+ @

BRB ... Mini Bars.....\$11.40..... \$8.55

- Designed especially for the Dawson Kiln-Sitter.
- Uniform shape makes consistent placement easy.
- Box of 50

1-11 @ 12+ @

LRB ... Large Cones\$13.15..... \$9.87

- The original pyrometric cones.
- Used to visually monitor firing progress and heatwork throughout the kiln through viewing (peep) ports.
- Need to be supported by cone plaques, clay pats, or wire cone holders.
- Uniform mounting height & angle - very important!
- We stock cones 012 - 13
- Box of 50

1-11 @ 12+ @

SSB .. Self-Supporting Cones \$9.40..... \$7.05

- Preferred for use as witness cones on kiln shelves.
- Most accurate and easiest to use cones available.
- Box of 25

CHS Wire Cone Holders (bag of 5)

1-2 @ 3-5 @ 6-11 @ 12-23 @ 24+ @
 \$5.35 \$4.81 \$4.28 \$3.75 \$3.21

MS517 ... 3-Hole Cone Plaque (use with LRB cones)

When you buy ... **1-11 @ 12-49 @ 50+ @**
 \$1.50 \$1.48 \$1.20